



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

RESISTANCE TO UV RAYS

Beginning date : 21/12/2018

Analysis ending date : 25/01/2019

Test environment:

- **Temperature:** 23 °C
- **Atmospheric pressure:** 1010 mbar
- **Relative humidity:** 50 %

Test data:

- **Duration of the test** : 840 h (35 days)
- **Test chamber temperature** : 60 ± 2 °C
- **Exposure** : 24 hours on 24 to UV-A
- **Radiation** : 0,76 W/m² a 340 nm

Examiner Dr. Falanga Giacomo	Metallurgy Dept. Responsible D. Marzulli Maunzio	MODENA CENTRO PROVE Director Sant'Unione dr. Giuseppe
--	--	--

Results after the test:

Sample	Inspection interval	Observations
Artificial lichen	1 week	No color variation
	2 weeks	No color variation
	3 weeks	No color variation
	4 weeks	No color variation
	5 weeks	At the end of the test sample doesn't show any alteration of the color and no degradation of the material
Buxus 3D purple big	1 week	No color variation
	2 weeks	No color variation
	3 weeks	No color variation
	4 weeks	No color variation
	5 weeks	At the end of the test sample doesn't show any alteration of the color and no degradation of the material
Buxus 3D purple small	1 week	No color variation
	2 weeks	No color variation
	3 weeks	No color variation
	4 weeks	No color variation
	5 weeks	At the end of the test sample doesn't show any alteration of the color and no degradation of the material
Aloe vera	1 week	No color variation
	2 weeks	Slight loss of brightness of the tested surface
	3 weeks	The sample is darker than the new sample
	4 weeks	No significant change
	5 weeks	At the end of the test, the sample presents a visible loss of gloss and the coloring is darker than the untested sample
Purple leaves	1 week	No color variation
	2 weeks	No color variation
	3 weeks	No color variation
	4 weeks	No color variation
	5 weeks	At the end of the test sample doesn't show any alteration of the color and no degradation of the material

Examiner Dr. Falanga Giacomo	Metallurgy Dept. Responsible P. Marzocchi Marzio	MODENA CENTRO PROVE Director Sant'Unione dr. Giuseppe
-------------------------------------	---	---



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 40123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

Sample photos at the end of the test:



Artificial lichen



Buxus 3D purple big

Examiner
Giacomo Falanga
Dr. Falanga Giacomo

Metallurgy Dept. Responsible
Maranelli Maunzio
p.i. Maranelli Maunzio

MODENA CENTRO PROVE
Giuseppe Sant'Unione
Director
Sant'Unione dr. Giuseppe



Buxus 3D purple small



Aloe vera



Purple leaves

<p>Examiner Dr. Falanga Giacomo</p>	<p>Metallurgy Dept. Responsible P.i. Maranelli Maunzio</p>	<p>MODENA CENTRO PROVE Director Sant'Unione dr. Giuseppe</p>
--	---	---